



Infrastructure Technology

Materials Science & Engineering, Graham Road (PO Box 56), Highett, Victoria, Australia 3190
Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Email: tiles@csiro.au Web: <http://www.cmse.csiro.au>

Registered Testing Authority - CSIRO

24 September 2014

Our Ref. EN13 / 1637 03/0212

TEST REPORT No. 7172.3s

Requested by: The Andrews Group
62 River Street
South Yarra
VIC 3141
on (date): 17 September 2014
Manufacturer: BOLON
Product Desc.: BOLON Woven Vinyl: Elliptical Yarn

Sampling details:
Where: Delivered
Date: 17 September 2014
By whom: Courier
How (methods): N/A

The results reported relate only to the sample(s) tested and the information received. No responsibility is taken for the accuracy of the sampling unless it is done under our own supervision. CSIRO cannot accept responsibility for deviations in the manufactured quality and performance of the product. While CSIRO takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes. CSIRO will not be responsible for the results of any actions taken by the client or any other person on the basis of the information contained in the report or any opinions expressed in it. The reproduction of this test report is only authorised in the form of a complete photographic facsimile. Our written approval is necessary for any partial reproduction.

This test report consists of 5 pages

SUMMARY OF SLIP RESISTANCE TESTS PERFORMED:

		Result	Class
AS 4586:2013	Slip resistance classification of new pedestrian surface materials		
	Appendix A: WET Pendulum (Slider 96). Mean SRV:	29	P2 (Y*)
	Appendix B: DRY (FFT). Mean COF:	0.70	D1 (F*)
	Appendix A,B: Dual classification:		P2 (Y*),D1 (F*)
AS 4586:2013	Slip resistance classification of new pedestrian surface materials,		
	Appendix D: OIL-WET Ramp		
	Corrected mean overall acceptance angle:	12°	R 10
	(*) = AS 4568:2004 classification		

In order to interpret the classifications, please refer to Standards Australia Handbook 198, An Introductory Guide to the Slip Resistance of Pedestrian Surface Materials, which recommends minimum classifications for a wide variety of locations.

It is important to realise that test results obtained on unused factory-fresh samples may not be directly applicable in service, where proprietary surface coatings, contamination, wear and subsequent cleaning all influence the behaviour of the pedestrian surface.



REPORT NO: 7172.3s
ISSUE DATE: 24 September 2014
MANUFACTURER: BOLON
PRODUCT DESC: BOLON Woven Vinyl: Elliptical Yarn

Page 2 of 5

SLIP RESISTANCE CLASSIFICATION OF NEW PEDESTRIAN SURFACE MATERIALS

WET PENDULUM TEST METHOD

TEST CARRIED OUT IN ACCORDANCE WITH
AS 4586:2013 (Appendix A)

Test Date: 18 September 2014

RESULTS:	Location:	Slip Resistance Laboratory	Slider used: 96
	Sample:	Unfixed	Conditioned with grade P400 paper, dry
	Cleaning:	Deionized water	
	Temperature:	23°C	

Pendulum Friction Tester: Stanley (S/N: 0312, calibrated 03/06/2014)
Test conducted by: Andy Giang

	Specimen				
	1	2	3	4	5
Last 3 swings (BPN)	34	30	29	29	27
	33	29	29	29	27
	33	29	29	29	27
Averages	33	29	29	29	27

Mean SRV : 29

CLASS :

P2 (Y*)

(*) = AS 4568:2004 classification



REPORT NO: 7172.3s
ISSUE DATE: 24 September 2014
MANUFACTURER: BOLON
PRODUCT DESC: BOLON Woven Vinyl: Elliptical Yarn

Page 3 of 5

SLIP RESISTANCE CLASSIFICATION OF NEW PEDESTRIAN SURFACE MATERIALS

DRY FLOOR FRICTION TEST METHOD

TEST CARRIED OUT IN ACCORDANCE WITH
AS 4586:2013 (Appendix B)

Test Date: 18 September 2014

RESULTS Location: Slip Resistance Laboratory
Sample Sample Unfixed
Cleaning: Dry el/static cloth
Temperature: 23°C
FFT measurements taken over 2 passes of 800mm each
Slider 96
Conditioned with grade P400 paper, dry

Floor Friction Tester: Tortus Mk II (S/N: 224)
Test conducted by: Andy Giang

Run 1: Average COF: 0.69
Run 2: Average COF: 0.70
Mean COF: 0.70

According to AS 4586 the Dry Coefficient of Friction shall be reported as :
(mean rounded to the nearest 0.05)

0.70

CLASS :

D1 (F*)

(*) = AS 4568:2004 classification



REPORT NO: 7172.3s
ISSUE DATE: 24 September 2014
MANUFACTURER: BOLON
PRODUCT DESC: BOLON Woven Vinyl: Elliptical Yarn

Page 4 of 5

SLIP RESISTANCE CLASSIFICATION OF NEW PEDESTRIAN SURFACE MATERIALS

OIL-WET RAMP TEST METHOD

TEST CARRIED OUT IN ACCORDANCE WITH
AS 4586:2013 (Appendix D)

Test Date: 24 September 2014

Location: Slip Resistance Laboratory Test conducted by: KH, AG

Sample Fixed

Joint width: 0 mm

Surface structure: ☐ Smooth
☒ Profiled
☐ Structured

RESULTS

Corrected mean overall acceptance angle: 12 °

Displacement space: not tested

CLASSIFICATION:

Slip Resistance Assessment Group:

R 10

Displacement Space Assessment Group:

-

Test shoe used: Uvex Athletic



Infrastructure Technology

Materials Science & Engineering, Graham Road (PO Box 56), Highett, Victoria, Australia 3190

Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Email: tiles@csiro.au Web: <http://www.cmse.csiro.au>

REPORT NO: 7172.3s
ISSUE DATE: 24 September 2014
MANUFACTURER: BOLON
TILE DESC: BOLON Woven Vinyl: Elliptical Yarn

Page 5 of 5

Date and Place 24 September 2014, Highett, Vic

Name, Title and Digital Signature:



ANDY GIANG
Technical Officer
Tel: 61 3 92526000
Fax: 61 3 92526244
Email: Andy.Giang@csiro.au